



Ciba® IRGANOX® 1076

Phenolic Primary Antioxidant for Processing and Long-Term Thermal Stabilization

Characterization	IRGANOX 1076, a sterically hindered phenolic antioxidant, is highly efficient, non discoloring stabilizer for organic substrates such as plastics, synthetic fibers, elastomers, adhesives, waxes, oils and fats. It protects these substrates against thermo-oxidative degradation. IRGANOX 1076 is odorless, stable to light and has excellent color retention. It has good compatibility with most substrates, low volatility and high resistance to extraction.	
Chemical name	Octadecyl-3-(3,5-di-tert.butyl-4-hydroxyphenyl)-propionate	
CAS number	2082-79-3	
Structure		
Molecular weight	531 g/mol	
Applications	IRGANOX 1076 can be applied in polyolefins such as polyethylene, polypropylene, polybutene-1 as well as in other polymers such as engineering plastics, styrene homo- and copolymers, polyurethanes, elastomers, adhesives, and other organic substrates.	
Features/benefits	IRGANOX 1076 can be used in combination with other additives such as costabilizers (e.g. thioesters, phosphites, phosphonites), light stabilizers, and other functional stabilizers. The effectiveness of the blends of IRGANOX 1076 with IRGAFOS 168 (IRGANOX B-blends) or with IRGAFOS 168 and Lactone HP-136 (IRGANOX HP- products) is particularly noteworthy.	
Product forms	<i>Code:</i> <i>Appearance:</i>	IRGANOX 1076 White fine granules, powder FF: white, free-flowing granules FD: white, free-flowing, dust free pastilles Melt: clear liquid

Guidelines for use	<p>500 ppm - 2000 ppm of IRGANOX 1076 provide long-term thermal stability to the polymer. Concentrations up to several percent can be used depending on the substrate and the requirements of the end application.</p> <p>In polyolefins the concentration levels for IRGANOX 1076 range between 0.1% and 0.4% depending on substrate, processing conditions and long-term thermal stability requirements. The optimum level is application specific.</p> <p>IRGANOX 1076 is recommended for styrene homo- and copolymers at a concentration level ranging from 0.1 to 0.3 %.</p> <p>Concentration levels of IRGANOX 1076 in hot melt adhesives range from 0.2% to 1% and in synthetic tackifier resins between 0.1% and 0.5%.</p> <p>Extensive performance data of IRGANOX 1076 in various organic polymers and applications are available upon request.</p>	
Physical Properties	<i>Melting Range</i>	50 - 55°C
	<i>Flashpoint</i>	273°C
	<i>Vapor Pressure (20 °C)</i>	2.5 E-7 Pa
	Solubility (20 °C)	% w/w
	<i>Water</i>	< 0.01
	<i>Acetone</i>	19
	<i>Benzene</i>	57
	<i>Chloroform</i>	57
	<i>Cyclohexane</i>	40
	<i>Ethanol</i>	1.5
	<i>Ethylacetate</i>	38
	<i>n-Hexane</i>	32
	<i>Methanol</i>	0.6
	<i>Toluene</i>	50
	Volatility	
	<i>(TGA, in air at 20°C/ min)</i>	
	<i>Temp. at 1% weight loss</i>	230°C
	<i>Temp. at 10% weight loss</i>	288°C
Handling & Safety	In accordance with good industrial practice, handle with care and prevent contamination of the environment. Avoid dust formation and ignition sources. For more detailed information please refer to the material safety data sheet.	
Registration	IRGANOX 1076 is listed on the following Inventories:	
	Australia	AICS
	Canada	DSL
	China	IECSC
	Europe	EINECS
	Japan	ENCS
	Korea	ECL
	New Zealand	TSA
	Philippines	PICCS
	Switzerland	BUWAL
	USA	TSCA
	IRGANOX 1076 is approved in many countries for use in food contact applications. For detailed information refer to our Positive List or contact your local sales office.	

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for the intended conditions of use. The product(s) has (have) not been tested for, and is (are) therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended. Please note that products may differ from country to country. If you have any queries, kindly contact your local Ciba Specialty Chemicals representative. Further information at website: <http://www.cibasc.com>